

BreezeBond™ Product Bulletin

Decorative Paper

Features and Performance

BreezeBond™ is a low viscosity, soy-based adhesive made up of water, modified soy flour, and low environmental-impact inorganic additives for decorative hot-press/roller/laminator applications with the following characteristics:

- Single component adhesive
- Suitable for indoor applications
- High Solids
- Low Viscosity
- Strong wet bond strength
- No detectable formaldehyde
- Competitive with current overlay adhesives in the market
- Compostable

Physical Properties

Adhesive capabilities: Average wet strength 896 psi (6.18 MPa)
Color: Light yellow to beige when wet, almost white when dry.
Viscosity: 2.02-3.36 lb_m/ft-second (3000-5000 mPa-s, centipoise)
Density: 8.3 lb/gal (1.00 g/cm³), **pH:** 8.0-8.5
Solids Content: Can be provided at up to 50%
VOC Content: Less than 0.008 ppm
VHAP Content: Not Applicable
Hot Press Time: 20-50 sec @ 30 psi (.186 MPa) minimum
Spreader Rate: 0.7-0.8 oz/ft² (21.4–24.4 mg/cm²)

General Usage Instructions

To be stored at near room temperature (68-77 °F, 20-25 °C). Prolonged exposure to elevated temperatures (140 °F, 50 °C) can lead to partial degradation.

For maximum wet adhesion strength and higher viscosity, an additive can be mixed into the adhesive prior to application. Contact the BreezeBond™ team at Specialty Organics, Inc. for more information.

Application

- 1) Mix the adhesive to give it a homogenous consistency before application.
- 2) Apply the adhesive to the substrate (spray, roller, rubber blade / squeegee).
- 3) Bring the paper and substrate together with your preferred heated roller/laminator technique.
- 4) Slowly apply paper at 257 °F (125 °C) minimum. Rougher surfaces require longer time/slower roll rate.

Storage/Shelf Life

- Expected shelf life of up to three months when stored in a sealed container at room temperature. Keep away from direct sunlight. Avoid elevated temperatures.
- Keep container tightly sealed to prevent moisture from leaving the mixture.
- After long periods of storage, stirring is recommended prior to use.

Clean-up/Disposal

- Use hot water while the adhesive residue is still wet in the container/mixer/holding tank.
- Removal of dried adhesive requires a water soak followed by a high-pressure water jet.
- This adhesive is compatible with most local sewage treatment methods, however, check with local authorities for proper waste disposal.



BreezeBond™
Specialty Organics Inc.
16276 Koala Road
Adelanto, CA 92301
www.soichem.com

Warranty, Limited Remedy and Disclaimer: Specialty Organics, Inc. warrants that our products meet the applicable product specification at the time of shipment. If the product does not meet this warranty, it is our option to replace the product or refund the purchase price. Unless an additional warranty is specifically stated, Specialty Organics, Inc. does not provide any other warranties, express or implied. The user is solely responsible for evaluating the suitability of this product and determining whether it is fit for a particular product and method of application. Limitation of Liability: Except where prohibited by law, Specialty Organics, Inc. will not be liable for any loss or damage arising from the use of our product.
Protected under U.S. Patent # US 9,353,300 B2